



800-800-5737



866-874-8070

## Product Data: Trojan Beta-Z Wood Sealer #60-65

<b>Product Description</b>	A unique water-based polyester polymer, polyurethane and acrylic formula manufactured for the effective and safe treatment for the preservation of all wood surfaces. This sealer is intended to be used before the application of paint or other top coats. This sealer effectively holds finish coats of paint on the surface thereby requiring less top coat.
<b>Typical Uses</b>	For industrial, commercial and residential use. <b>Trojan Beta-Z Wood Sealer</b> is a safe, low V.O.C. sealer for contractors, painters and hobbyists.
<b>Product Advantages</b>	<p><b>Trojan Beta-Z Wood Sealer</b></p> <ul style="list-style-type: none"> <li>* Non-Toxic   * Non-Flammable   * No Solvents   * Satin Finish   * Low V.O.C.</li> <li>* Penetrates   * Water Clean-up   * Mild Aroma</li> </ul>
<b>Appearance</b>	Milky in Container—Dries Clear with Satin Finish
<b>Physical Constants</b>	<p><b>Specific Gravity:</b> (H20=1) 1.10@ 20 Deg C.  <b>Solubility in Water:</b> Soluble  <b>Evaporation Rate:</b> Same as water  <b>pH:</b> 6.8  <b>Storage:</b> 40-90 deg. F  <b>Percent Solids by Weight:</b> 13%  <b>V.O.C.:</b> (Extremely Low) 11.67 g/L</p>
<b>Coverage Rate</b>	200/ sq. ft./ gallon (depends on roughness of surface & degree of porosity)
<b>Sold in</b>	<p>1-Gallon Bottles            5-Gallon Pails            55-Gallon Drums</p>



Envirosafe Manufacturing Corp.™  
 East Coast: 7634-B Progress Circle  
 Melbourne, FL 32904  
 800-800-5737  
 West Coast: 817 Benton Way  
 Wenatchee, WA 98801  
 509-662-9204

**Web Sites**  
[www.envirosafemfg.com](http://www.envirosafemfg.com)  
[www.eco-wares.com](http://www.eco-wares.com)

*Products that get the job done!*

## TROJAN BETA-Z WOOD SEALER #60-65

**Limitations:** Apply in good weather when air and surface temperatures are above 45 deg. F. Temperature must remain above 40 deg. F for 24 hours after application. For optimum application properties, materials should be between 70 to 100 deg. F prior to application. Maintain unused materials in closed containers in protected storage at 40 to 100 deg. F.

**Surface Preparation:** Good surface preparation is essential to a satisfactory coating application. Surfaces to be coated should be clean and dry. Remove all dirt, dust, oil, grease, mildew, rust, loose or cracked paint or other contamination by spraying with either mechanical means or using **Enviro Clean Degreaser**. **Mixing:** Trojan Beta-Z Wood Sealer is a one component coating. Use as it comes from the container.

**Thinning:** This product is supplied at normal viscosity. Do Not add water. Adding water will affect the product quality and should not be done.

**Application:** Apply with a low pressure sprayer and back roll to even out the application or use brush and roller. Trojan Beta-Z should be liberally applied to allow the surface to absorb as much as it can without leaving puddles. Once dry, the surface may be coated with **Envirosafe Elastomeric Coating** (vertical surfaces) or painted with **Clear Armor Coat for Wood** or any acrylic or oil based paint.

**Cleanup:** Clean all equipment immediately after use with warm soapy water. Completely flush all spray equipment with soapy solution and rinse well.

**Safety:** Safe storage, handling and use dictate that adequate health and safety precautions be observed with this product. User is specifically directed to consult the current Material Safety Data Sheet for this product as well as precautions contained on product labeling.

**Notice:** The technical data contained herein is true and accurate to the best of our knowledge. All products are offered and sold subject to **Envirosafe Manufacturing Corporations** Standard Conditions of Sale. Published Technical data and instructions are subject to change without prior notice.